

copy 28
C
6060

AECD - 2223
LADC - 450

UNITED STATES ATOMIC ENERGY COMMISSION

PREPARATION OF BORON TRIFLUORIDE FOR USE IN NEUTRON COUNTERS

by

W. Hodges
M. I. Lloyd
B. Weinstock

Los Alamos Scientific Laboratory

DECLASSIFICATION STATEMENT A
Approved for public release
Distribution Unlimited

Date Declassified: August 9, 1948

Issuance of this document does not constitute authority for declassification of classified copies of the same or similar content and title and by the same authors.

Technical Information Branch, Oak Ridge, Tennessee
AEC, Oak Ridge, Tenn., 2-9-49--850-A4636

Printed in U.S.A.
PRICE 5 CENTS

DTIC QUALITY INSPECTED 4

NOTICE

This document is the property of the United States Government. It is furnished on a loan basis and shall be returned as specified, or upon recall by ASTIA to the following address: ASTIA Reference Center, Technical Information Division, Library of Congress, Washington 25, D.C.

19970205 127

U.S. GOVERNMENT
OFFICE OF RESEARCH
AND TECHNICAL SERVICES
101 MILLER
WASHINGTON, D.C.

PREPARATION OF BORON TRIFLUORIDE FOR USE IN NEUTRON COUNTERS

By W. Hodges, M. I. Lloyd, and B. Weinstock

INTRODUCTION

Boron trifluoride is used as the filling gas in ionization chambers and in proportional counters used for counting neutrons. The predominant reaction in these chambers is the $(n-\alpha)$ reaction on B^{10} with thermal neutrons.

Since the performance of counters filled with BF_3 is strongly dependent on the quality of the gas, an understanding of this dependence is helpful. While this subject is by no means completely understood, the following discussion summarizes some general information pertinent to this question.

One feature of a neutron counter which is generally desirable is a high counting efficiency, i.e., where a large percentage of the neutron flux gives rise to reaction. Since the number of neutrons captured is proportional to the concentration of B^{10} atoms in the chamber, by increasing the pressure of gas in the chamber, the efficiency can be increased. However, when the pressure is increased, higher voltages are necessary to collect the electrons. The use of higher voltages may then result in gas discharge in the counter, which will give rise to spurious counts. This is particularly true when small amounts of air and SiF_4 are present as impurities. By the use of BF_3 of increased B^{10} concentration (boron of over 80% B^{10} concentration is available), the necessity of using increased pressure to obtain higher efficiencies is somewhat alleviated. However the presence of impurities in the gas further manifest themselves by giving rise to poor operating characteristics. When pure BF_3 is used in a counter, good voltage and bias plateaus are obtained. The pulses tend to be more uniform in size and well separated above the noise background. With impurities in the BF_3 , this situation degenerates to the point where the counter cannot be reliably used.

The interior of the counter must be chemically clean before filling with BF_3 . The presence of water in the interior is particularly objectionable. Water is known to form a hydrate with BF_3 which hydrolyzes with the liberation of HF. HF can then react with any glass present in the counter to form SiF_4 and more water. This chain process can then continue until the performance of the counter is no longer reliable.

The use of organic gaskets and wax seals in the construction of BF_3 counters is generally objectionable. This is due to the fact that BF_3 reacts readily with organic substances of this type. The reaction products from such processes will then interfere with the operation of the counter.



If an accurate knowledge of the B^{10} concentration in the chamber is desired, the isotopic concentration of the gas must also be accurately known. Aside from gas of enriched B^{10} concentration, where a direct measurement of the isotopic ratio is necessary, the use of the reported value of 18.4% as the percentage of B^{10} in normal boron is somewhat unreliable. This is due to the relatively large fractionation which can occur in processing boron compounds. Even commercial tanks of BF_3 from the same company have shown differences in isotopic content of 1-2%. In addition to these possible corrections for the isotopic abundance, the molecular weight of BF_3 vapor has been found to depend to a small extent on the temperature and pressure.* This correction should also be made in precise calculations.

* Fisher and Wiedemann, Z. Allgem. Chem. 213, 106-114, (1933).

METHOD OF PREPARATION

The method of preparation which will be described has yielded BF_3 of the best known quality for use in neutron counters. It consists essentially of converting BF_3 into calcium fluoborate and subsequently regenerating the BF_3 by the thermal decomposition of this compound. The method was suggested by the fact that small samples of boron of enriched B^{10} concentration were available as the dimethyl ether compound for conversion into BF_3 . This compound is readily converted to calcium fluoborate. The method has the additional advantages of giving high yields (over 85%) and requiring simple inexpensive apparatus.

The conversion from tank BF_3 to purified BF_3 will be described below. The process can be summarized by the three equations:



Step 1

Boron Trifluoride, as obtained commercially, is about 90% pure, containing varying amounts of SiF_4 , HF, and air. By the formation of $\text{BF}_3 \cdot \text{Me}_2\text{O}$ these impurities are substantially removed except for small amounts dissolved in the ether compound. The apparatus which is used is shown in Figure 1.

The two gases are admitted simultaneously to the evacuated reaction bulb. The rates of flow of the gases can be judged roughly by means of the safety manometers and are regulated by means of the needle valves. The reaction bulb is cooled continuously with water because of the large amount of heat liberated by this reaction. When the system becomes "gagged" because of the accumulation of inert gas, it can be evacuated through the pump stopcock. The ether compound obtained is a colorless liquid and has a density given by the empirical relation $d = 1.603 - 0.00124T$ (T = degrees absolute).^{*} The liquid obtained can be stored in a ground glass stoppered bottle (the joint should be greased to prevent its freezing). It will gradually darken with time due to decomposition, but this has not been found detrimental to its subsequent use.

Step 2

The apparatus used for the conversion of $\text{Me}_2\text{O} \cdot \text{BF}_3$ into calcium fluoborate is shown in Figure 2. About 2 moles of CaF_2 are used per mole of ether compound. This represents a fourfold excess which is not entirely necessary. The CaF_2 is pumped on at about 300°C for a few hours in order to dry it. The presence of water in CaF_2 will lower the yield of BF_3 eventually obtained by an amount proportional to the quantity of water present. But, since CaF_2 usually contains only about 0.5% H_2O , thoroughly outgassing it is not considered an essential part of the procedure.

The ether compound reacts with the CaF_2 at a rapid rate at 100°C . In bringing the furnace up to temperature, it is found that the liquid is first absorbed by the CaF_2 at about 80°C , forming a slurry in the reaction flask. The reflux condenser is used to prevent serious loss of the ether compound, since the vapor pressure of the liquid is about 200 millimeters Hg at 100°C . The ether is collected in a graduated centrifuge tube kept at dry ice temperature. The yield as calculated from the amount of ether collected is about 93% when 10-20 cubic centimeter of liquid is used. The last traces of ether are pumped out of the reaction bulb before transferring it to the line for Step 3. The reaction bulb is kept at 100°C during this operation. The presence of any residual ether can be detected by putting dry ice on the U-tube. If the pressure in the system, as measured on the McLeod gauge, decreases when this is done, ether is still being liberated. Fluocarbon grease is used for the stopcocks on this line.

^{*} Report A-2120. "Separation of Isotopes", I. Kirshenbaum, N. Sabi, P. W. Schutz. The numerical values given in this discussion are all taken from this report.





Figure 1.

Figure 2. Apparatus used for the conversion of $Me_2O \cdot BF_3$ into calcium fluoborate.

The $\text{CaF}_2 \cdot \text{BF}_3$ compound forms a hard cake in the reaction flask, and the same bulb is therefore used for the next step.

Step 3

The thermal decomposition of the $\text{CaF}_2 \cdot \text{BF}_3$ compound is done with the apparatus shown in Figure 3. It is believed desirable to outgas the solid before generating and collecting the BF_3 . This is done to remove any residual SiF_4 which might remain in the mixture as well as to minimize the amount of air which might be trapped in the subsequent collection of the BF_3 . An arbitrary criterion is followed to determine when the solid has been sufficiently outgassed. The system is usually pumped on with the reaction bulb kept at 100°C until the pressure in the system becomes less than 10^{-3} millimeters Hg as measured on the McLeod gauge. The amount of BF_3 lost during this process is trivial since the decomposition pressure of the solid is quite small at 100°C .

The decomposition of the calcium fluoroborate is done at about 250°C . A plug of glass wool is kept in the neck of the decomposition flask to prevent any CaF_2 from blowing into the system. The first U-tube is kept at dry ice temperature, the BF_3 being collected in the second U-tube at liquid air temperature. A brown liquid, probably resulting from the decomposition of BF_3 due to the presence of water, is usually collected in the first U-tube. The system is pumped on at all times during the decomposition, since the solid has not been thoroughly degassed.

If the U-tube in which the BF_3 is being collected becomes plugged with BF_3 , the decomposition is stopped and the BF_3 transferred to the storage bulb. Fluocarbon stopcock grease is used in the decomposition line, while Apiezon M or N is used in the storage and pumping line.

The overall yield of BF_3 from Steps 2 and 3 is about 90%.

STORAGE OF BF_3 AND FILLING OF CHAMBERS

Because of the danger of fractionation in the preparation of BF_3 described, it is desirable to carry both of the steps to completion. This is particularly necessary if the gas is to be used as a relative standard representative of the total supply of starting material. Therefore, a suitable method of storage is necessary.

The gas has been successfully stored in a well outgassed glass bulb for many months at a time. Since BF_3 reacts with all the stopcock greases which we have tried and is inert to mercury, a mercury valve is used. The valve is shown in Figure 4 and consists of a U-tube with ground glass check valves. Vacuum and air are used to lower and raise the mercury in the reservoir. The stainless steel valve is included to facilitate any transfer operations as well as to provide a guard against failure of the check valves.

Chambers are always thoroughly outgassed before filling. They are pumped down to a "stick" vacuum on the McLeod, which must persist even after heating them. For fillings above atmospheric pressure, the metal system is used. The stainless steel valves used are repacked with poly TFE before being used with BF_3 . Chambers to be filled to atmospheric pressure or less are fitted with a glass semi-ball joint in order to attach them to the apparatus. Since BF_3 does not react rapidly with stopcock grease, Apiezon grease is used on the stopcocks in the filling line.

Well-constructed chambers filled with the gas may by this method have been found to show constant operational characteristics over long periods of time. In most instances these chambers are connected to the filling line with 1/8 inch copper tubing. The tubing is then pinched off and sealed closed after filling.

The gas in the 3-liter storage bulb is then completely vaporized before taking an aliquot to fill a chamber. It is necessary to freeze the BF_3 down into the cold finger in order to open the mercury valve. The system is usually pumped on at this point to remove any small amount of inert gas which may be present.




Figure 3. Apparatus used for the thermal decomposition of the $\text{CaF}_2 \cdot \text{BF}_3$ compound.




Figure 4. Mercury valve.

END OF DOCUMENT